



epiNITO

Technical Data Sheet

Insulating Varnish 2376

PRODUCT DESCRIPTION & CHARACTERISTIC

epiNITO Insulating Varnish 2376 is based on specially selected resin, linseed and tung oil combined with special additives to give a very fast drying and longer shelf life coating. Air dry between 1 – 2 hours. Product can also be forced dry to increase production speed.

- Very fast drying. It can be forced dried also.
- Good adhesion and good insulating properties.
- Good heat, water and corrosion resistance.
- Flexible coating.

SUGGESTED USES

It is suitable to use in:

- Motor rewinding industries.
- Electrical core and parts manufacturers.
- Transformer manufacturers.

SPECIFICATION

Non-Volatile content (wt)	30 ± 2 %
Specific Gravity	0.90 – 0.95 g/ml
Drying Time @ 27°C	Surface dry = 5 – 15 mins Touch dry = 15 – 30 hours Hard dry = 1 – 2 hours Forced dry = 100°C for 1 – 2 hours or 130°C for 0.5 – 1 hour
Heat Resistance	UP to 155°C
Thermal Class	Class F
Shelf Life	12 months
Colour Selection	Selected range. Typically; clear, golden yellow, golden,

The information in this document is given to the best of EPI's knowledge, based on laboratory testing and practical experience. EPI cannot accept liability for any damage, loss resulting from the use of this information. Users should always consult EPI for specific guidance on the usage of given data. EPI reserves the right to change the given data without further notice in order to comply with local requirements.



APPLICATION METHOD

By brushing, dipping, curtain coating, spraying or rolling.

FILM PROPERTIES

Adhesion	100/100 passed
----------	----------------

Break-down Voltage (ASTM D149):	
---------------------------------	--

- 130°C	160kV/mm
- 155°C	100kV/mm

Bend Test	3mm ϕ passed
-----------	-------------------

Impact Test	2 lb x 25" passed
-------------	-------------------

Pencil Hardness	HB+
-----------------	-----

Gloss	> 80GU
-------	--------

The information in this document is given to the best of EPI's knowledge, based on laboratory testing and practical experience. EPI cannot accept liability for any damage, loss resulting from the use of this information. Users should always consult EPI for specific guidance on the usage of given data. EPI reserves the right to change the given data without further notice in order to comply with local requirements.